







Report No.:

报告编号: HLDY20200814U02

TEST REPORT

检测报告

Name of Sample:

产品名称:

Rechargeable Li-ion Cell

可充电锂离子电芯

Model and Parameters:

型号参数:

18650 3.7V 1200mAh 4.44Wh

Classification of Test:

检测类别:

Commission test

委托检测

Issue Date:

签发日期:

2020.09.21

Tested by/测试

Reviewed by/审核

Approved by/批准

Test Engineer

anon Khan

Audit Engineer

Hongton Ku

Approval Engineer

Guangzhou MCM Certification & Testing Co., Ltd.

广州邦禾检测技术有限公司



General Information

一般信息

Application/申请单位:

Applicant: Xinxiang hongli supply source technology co., ltd

申请单位: 新乡市弘力电源科技有限公司

Address: Dayang Village South, zhaipo Town, Xinxiang, China

申请单位地址: 新乡县翟坡镇中大阳村南

Contact information: Tel: 13569411564

联系方式: E-mail: hldy5632158@163.com

General Information/基本信息:

Test item description: Rechargeable Li-ion Cell

产品名称: 可充电锂离子电芯

Classification: Lithium Ion Cell, Rechargeable

产品分类: 锂离子电芯,可充电

Trade Mark:

商标名称:

Model and parameters: 18650 3.7V 1200mAh 4.44Wh 型号参数:

Manufacturer: Xinxiang hongli supply source technology co., ltd

制造单位: 新乡市弘力电源科技有限公司

Address: Dayang Village South, zhaipo Town, Xinxiang, China

制造单位地址: 新乡县翟坡镇中大阳村南

Contact information: Tel: 13569411564

联系方式: E-mail: hldy5632158@163.com

Factory: Xinxiang hongli supply source technology co., Itd

生产单位: 新乡市弘力电源科技有限公司

Address: Dayang Village South, zhaipo Town, Xinxiang, China

生产单位地址: 新乡县翟坡镇中大阳村南

Testing Laboratory/测试实验室:

Laboratory: Guangzhou MCM Certification & Testing Co., Ltd.

测试单位: 广州邦禾检测技术有限公司

Address: 1 F No.13, Zhong San Section, ShiGuang Road, Panyu District, Guangzhou

测试单位地址: City, Guangdong Province, China.

中国广州市番禺区市广路钟三路段 13 号之一

Testing Location: As above

测试实验室地址: 同上

Test Specification/测试标准:

Standard: UN Manual of Tests and Criteria ST/SG/AC.10/11/Rev.6, amend1, section

测试标准: 38.3.

联合国《关于危险货物运输的建议书 试验和标准手册》

ST/SG/AC.10/11/Rev.6, amend1, section 38.3.

Procedure deviation:

■ None □ 38.3.3 (f) □ 38.3.3 (g)




General Product Information/产品通用信息:

The cell consists of the positive electrode plate, negative electrode plate, separator, electrolyte and case. The positive and negative electrode plates are housed in the case in the state being separated by the separator.

电芯由正极、负极、隔膜、电解液和外壳组成,正负极在封装前被隔膜所隔离。

Label/标签:



Technology Information 技术参数	Cell	Battery
Model 型号	18650	1
Nominal Capacity 额定容量(mAh)	1200	1
Nominal Voltage 额定电压(V)	3.7	1
Nominal Charge Current 额定充电电流(mA)	240	1
Nominal Discharge Current 额定放电电流(mA)	240	1
Maximum Charge Current 最大充电电流(mA)	1200	1
Maximum Discharge Current 最大放电电流(mA)	1200	1
Maximum Charge Voltage 最大充电电压(V)	4.20	1
Cut-Off Voltage 放电截至电压(V)	A 3.00 VIC	e i



Test Conclusion 测试结论						
Clause 条款	Test item 测试项目	Test Sample 测试样品	Test Result 测试结论	Remark 备注		
38.3.4.1	Altitude simulation 高度模拟		Р	1		
38.3.4.2	Thermal test 温度循环测试		Р	1		
38.3.4.3	Vibration 振动	C1#~C10#	Р	1		
38.3.4.4	Shock 冲击		Р	1		
38.3.4.5	External short circuit 外部短路		Р	1		
20246	Impact 重物冲击	C11#~C20#	Р	1		
38.3.4.6	Crush 挤压	1	N/A	1		
38.3.4.7	Overcharge 过充电		N/A	1		
38.3.4.8	Forced discharge 强制放电	C21#~C40#	Р	1		

Ambient Temperature:

环境温度:

Receiving Date:

样品接收日期:

Test Date:

测试时间:

20 ± 5°C

2020.09.01

2020.09.02 - 2020.09.17

Test conclusion/测试结论:

Technolo

The Rechargeable Li-ion Cells submitted by Xinxiang hongli supply source technology co., Itd have passed the test items of UNITED NATIONS' Recommendations on the Transport of Dangerous Goods, Manual of Test and Criteria ST/SG/AC.10/11/Rev.6, amend1, section 38.3.

由新乡市弘力电源科技有限公司送检的可充电锂离子电芯符合联合国《关于危险品货物运输的建 议书 试验和标准手册》ST/SG/AC.10/11/Rev.6,amend1,section 38.3 的要求。

Seal:

检测专用章:



UN Manual of Tests and Criteria ST/SG/AC.10/11/Rev.6, amend1, section 38.3.
联合国《关于危险货物运输的建议书试验和标准手册》ST/SG/AC.10/11/Rev.6, amend1, section 38.3.

Clause Requirement Result 结果 判断

38.3.2	Scope 范围	Р			
	All cell types shall be subjected to tests T.1 to T.6 and T.8. 所有电芯类型应该进行 T.1 到 T.6 和 T.8	Р			
	All non-rechargeable battery types, including those composed of previously tested cells, shall be subjected to tests T.1 to T.5. 所有不可充电电池,包括由测试合格的电芯组成的电池应该进行 T.1 到 T.5。	N/A			
	All rechargeable battery types, including those composed of previously tested cells, shall be subjected to tests T.1 to T.5 and T.7. 所有可充电电池,包括由测试合格的电芯组成的电池应该进行 T.1 到 T.5,以及 T.7 的测试。				
	In addition, rechargeable single cell batteries with overcharge protection shall be subjected to test T.7. 另外,有过充保护的可充单电芯电池应该进行 T.7 的测试。	N/A			
	A component cell that is not transported separately from the battery it is part of needs only to be tested according to tests T.6 and T.8. 不单独运输的作为配件的电芯进行 T.6 和 T.8 的测试。	N/A			
	A component cell that is transported separately from the battery it is part of needs only to be tested according to tests T.1 to T.6 and T.8. 单独运输的作为配件的电芯进行 T.1 到 T.6,以及 T.8 的测试。	Р			
	A cell or battery that is an integral part of the equipment it is intended to power that is transported only when installed in the equipment may be in accordance with the applicable tests when installed in the equipment. 作为设备组成部分的用作设备电源的电芯或电池,如果只能在设备中运输,可按照装在设备中的适用测试要求进行试验	N/A			
38.3.3(d)					
38.3.3(f)	When testing a battery assembly in which the aggregate lithium content of all anodes when fully charged, is not more than 500 g, or in the case of a lithium battery, with a Watt-hour rating of not more than 6 200Wh, that is assembled from batteries that have passed all applicable tests, one assembled battery in a fully charged state shall be tested under tests T3, T4 and T5, and in addition, test T7 in the case of a rechargeable battery. 当试验集成电池时,如果集成电池在完全充电时所有阳极的合计锂含量不大于 500g,或在锂离子电池组的情况下,额定瓦特小时不超过 6200Wh 时,并且是用通过所有试验的电池集合而成的,须对一个完全充电状态的集成电池做试验 T.3、T.4 和 T5,另外,如果是可充电电池,则还需进行 T.7 试验。	N/A			



UN Manual of Tests and Criteria ST/SG/AC.10/11/Rev.6, amend1, section 38.3. 联合国《关于危险货物运输的建议书试验和标准手册》ST/SG/AC.10/11/Rev.6, amend1, section 38.3.

Clause Requirement Result Verdict 特质

条款	要求	结果	判断
38.3.3(g)	When batteries that have passed all applicable tests are electrically connected to form battery in which the aggregate lithium content of all anodes, when fully charged more than 500g, or in the case of a lithium ion battery, with a Watt-hour rating of more than 6 200Wh, the assembled battery does not need to be tested if the assembled battery is of a type that has been verified as preventing: - Overcharge; - Short circuits; and - Over discharge between the batteries 对于已通过所有适用试验的若干电池组成的集成电池,如在完全充电时所有阳极的总锂含量超过 500g,或在锂离子电池的情况下,如额定的瓦特-小时数超过 6200Wh 时,当集成电池如经过验证属于可防止下列情况,即无需进行试验: - 过充电: - 短路; 且 - 电池之间的过放	Not battery assembly 非集成电池	N/A
38.3.4	Procedure/程序		Р
	Test T.1 to T.5 shall be conducted in sequence on the same cell or battery. 小型电芯或电池应按顺序进行试验 T.1至 T.5。 Test T.6 and T.8 shall be conducted using not otherwise tested cells or batteries. 试验 T.6 和 T.8 应使用未试验过的电芯或电池。 Test T.7 may be conducted using undamaged batteries previously used in tests T.1 to T.5 for purpose of testing on cycled batteries. 试验 T.7 可以使用原先在试验 T.1 至 T.5 中使用过的未损坏电池进行。	ce	Р
38.3.4.1	Altitude Simulation/ 高度模拟		P
	Test simples shall be stored at a pressure of 11.6kPa or less for at least six hour at ambient temperature (20±5℃). 试验电芯和电池在环境温度(20±5℃)下,储存在小于等于11.6kPa 的压力下至少 6 小时。		Р
	Results: no leakage, no venting, no disassembly, no rupture, no fire, and the open circuit voltage drop not less than 90%. 试验结果: 无泄漏、无排气、无解体、无破裂、无着火和开路电压降不低于 90%。	See the TABLE: 38.3.4.1	Р
	The requirement relating to voltage is not applicable to test cells and batteries at fully discharge states. 测试电压的要求不适用于完全放电的电芯和电池。		N/A
38.3.4.2	Thermal Test/温度试验		Р



यरण∧	文介	2000	7707
	Test cells and batteries are to be stored for at least six hours at a test temperature equal to 72±2°C, followed by storage for at least six hours at a test temperature equal to -40±2°C, The maximum time interval between test temperature extremes is 30 minutes, This procedure is to be repeated until 10 total cycles are complete, after which all test cells and batteries are to be stored for 24 hours at ambient temperature (20±5°C). For large cells and batteries the duration of exposure to the test temperature extremes should be at least 12hours 将电芯和电池在温度为 72±2°C 的条件下贮存不少于 6 个小时; 然后,在温度-40±2°C 条件下贮存不少于 6 个小时; 两个温度间的间隔最长为 30min,重复操作上述步骤到 10 次; 然后,在环境温度为 20±5°C 的条件下放置 24 个小时。	Stored for 6h at 72±2°C and -40±2°C 在 72±2°C 与 -40±2°储存 6 个小时	P
	Results: no leakage, no venting, no disassembly, no rupture, no fire, and the open circuit voltage drop not less than 90%. 试验结果: 无泄漏、无排气、无解体、无破裂、无着火和开路电压降不低于 90%。	See the TABLE: 38.3.4.2	Р
	The requirement relating to voltage is not applicable to test cells and batteries at fully discharge states. 测试电压的要求不适用于完全放电的电芯和电池。	1	N/A
38.3.4.3	Vibration/振动		Р
	For cells and small batteries: from 7 Hz a peak acceleration of 1gn is maintained until 18 Hz reached. The amplitude is then maintained at 0.8mm (1.6mm total excursion) and the frequency increased until a peak acceleration of 8gn occurs (approximately 50Hz). A peak acceleration of 8gn is then maintained until the frequency is increased to 200Hz. 对于电芯和小电池: 保持峰值加速度 1gn,从 7Hz 到 18Hz。然后振幅保持在 0.8mm(总偏移量为 1.6mm),增加频率,直到峰值加速度达到 8gn(约 50Hz)。然后保持8gn 的峰值加速度,直到频率增加到 200Hz。	ce	Р
	For large batteries: from 7 Hz to a peak acceleration of 1gn is maintained until 18 Hz reached. The amplitude is then maintained at 0.8 mm (1.6 mm total excursion) and the frequency increased until a peak acceleration of 2gn occurs (approximately 25 HZ). A peak acceleration of 2gn is then maintained until the frequency is increased to 200 Hz. 对于大电池: 保持峰值加速度 1gn, 从 7Hz 到 18Hz。然后振幅保持在 0.8mm(总偏移量为 1.6mm),增加频率,直到峰值加速度达到 2gn(约 25Hz)。然后保持 2gn 的峰值加速度,直到频率增加到 200Hz。		N/A
	Results: no leakage, no venting, no disassembly, no rupture, no fire, and the open circuit voltage drop not less than 90%. 试验结果: 无泄漏、无排气、无解体、无破裂、无着火和开路电压降不低于 90%。	See the TABLE: 38.3.4.3	Р



UN Manual of Tests and Criteria ST/SG/AC.10/11/Rev.6, amend1, section 38.3. 联合国《关于危险货物运输的建议书试验和标准手册》ST/SG/AC.10/11/Rev.6, amend1, section 38.3.

Clause Requirement Result Verdict 条款 要求 结果 判断

大沃	安	4年	判断
	The requirement relating to voltage is not applicable to test cells and batteries at fully discharge states. 测试电压的要求不适用于完全放电的电芯和电池。		N/A
38.3.4.4	Shock/冲击		Р
	- Each cell shall be subjected to a half-sine shock of peak acceleration of 150gn and pulse duration of 6 milliseconds. Alternatively, large cells may be subjected to a half-sine shock of peak acceleration of 50gn and pulse duration of 11 milliseconds. 每一个电芯应承受峰值加速度为 150gn、脉宽为 6 毫秒的半正弦冲击。或者,大电芯可以按峰值加速度为 50gn、脉宽为 11 毫秒的半正弦冲击。		Р
	- Each battery shall be subjected to a half-sine shock of peak acceleration depending on the mass of the battery. The pulse duration shall be 6 milliseconds for small batteries and 11 milliseconds for large batteries. 每个电池应承受的峰值加速度取决于电池的质量。小电池的脉宽应为 6 毫秒,大电池的脉宽应为 11 毫秒。		N/A
	Each cell or battery shall be subjected to three shocks in the positive direction and to three shocks in the negative direction in each of three mutually perpendicular mounting positions of the cell or battery for a total of 18 shocks. 每一个电芯或电池在安装位置的 3 个垂直的轴向的正方向和负方向各进行 3 次冲击,总共 18 次。		Р
	Results: no leakage, no venting, no disassembly, no rupture, no fire, and the open circuit voltage drop not less than 90%. 试验结果: 无泄漏、无排气、无解体、无破裂、无着火和开路电压降不低于 90%。	See the TABLE: 38.3.4.4	Р
	The requirement relating to voltage is not applicable to test cells and batteries at fully discharge states. 测试电压的要求不适用于完全放电的电芯和电池。		N/A
38.3.4.5	External Short Circuit/外部短路		Р
	The cell or battery to be tested shall be heated for a period of time necessary to reach a homogeneous stabilized temperature of 57±4°C, measured on the external case. 待测电芯或电池应加热一段时间,以稳定均衡在 57±4°C 的温度,并测量外壳上的温度。		Р
	The exposure time shall be at least 6 hours for small cells and small batteries, and 12 hours for large cells and large batteries. 小电芯或小电池的暴露/加热时间应至少为 6 小时,大电芯或大电池的暴露/加热时间应至少为 12 小时。		Р



オマラ人	安水	升列西汀					
	Then the cell or battery at 57± 4°C shall be subjected to one short circuit condition with a total external resistance of less than 0.1 ohm.	P					
	然后,在 57±4°C 下的电芯或电池应经受一次短路,外部线路总的电阻小于 0.1 欧姆。						
	This short circuit condition is continued for at least one hour after the cell or battery external case temperature has returned to 57 ± 4°C, or in the case of the large batteries, has decreased by half of the maximum temperature increase observed during the test and remains below that value. 在电芯或电池外部外壳温度恢复到 57±4°C 后,短路状态继续持续至少一小时,或对于大电池的情况下,降至试验期间观察到的最大温升的一半,并保持在该值以下。						
	The short circuit and cooling down phases shall be conducted at least at ambient temperature. 短路和冷却阶段应至少在环境温度下进行。						
	Results: external case temperature does not exceed 170°C and there is no disassembly, no rupture and no fire during the test and within six hours after the test. 试验结果: 外部温度不超过 170°C,试验期间和试验后 6 小时内,无解体、破裂或起火现象。	Р					
38.3.4.6	Test T.6: Impact, Crush/重物冲击,挤压	Р					
38.3.4.6.2	Impact/重物冲击						
	Applicable to cylindrical cells not less than 18.0 mm in diameter. 适用于直径不小于 18.0 mm 的圆柱型电芯						
	The test cell is placed on a flat smooth surface. A stainless steel bar (type 316 or equivalent) (Ø 15.8 mm ±0.1mm, length: ≥60 mm or of the longest dimension of the cell, whichever is greater) is placed across the centre of the test sample. 试验电芯放置平坦表面上。一根直径为 15.8± 0.1 毫米,长度至少 6 厘米(或该电芯的最大尺寸,以较大者为准)的 316 型不锈钢棒横放在样品的中心。	Р					
	A mass of 9.1 kg ±0.1 kg is dropped from a height of 61cm± 2.5cm at the intersection of the bar and the test sample in a controlled manner using a near frictionless, vertical sliding track or channel with minimal drag on the falling mass. 一个重达 9.1 ± 0.1 千克的铁锤从 61±2.5 厘米高处以几乎无摩擦和零拉力的姿态沿垂直轨道或通道跌落至不锈钢棒与样品的交结点上。	Р					



Report No. / 报告编号: HLDY20200814U02 UN Manual of Tests and Criteria ST/SG/AC.10/11/Rev.6, amend1, section 38.3. 联合国《关于危险货物运输的建议书试验和标准手册》ST/SG/AC.10/11/Rev.6, amend1, section 38.3. Clause Requirement Result Verdict 条款 要求 结果 判断 The test sample is to be impacted with its longitudinal axis parallel to the flat surface and perpendicular to the longitudinal axis of the steel bar lying across the centre of the test sample. P Each sample is to be subjected to only a single impact 被撞击的测试样品的长轴平行于平面,并与横放在样品中心的不 锈钢棒垂直,每只样品只经受一次撞击。 38.3.4.6.3 Crush/挤压 N/A Applicable to prismatic, pouch, coin/button cells and cylindrical cells less than 18.0 mm in diameter 适用于棱柱形、袋形、硬币/纽扣式电池和直径小于 18.0 mm 的圆柱型电芯。 A cell or component cell is to be crushed between two flat surfaces. The crushing is to be gradual with a speed of approximately 1.5cm/s at the first point of contact. N/A 在两个平面间对电芯或元件电芯进行挤压,挤压在第一个接触点 的速度约为 1.5cm/s。 The crushing is to be continued until the first of the three options below is reached. (a) The applied force reaches 13kN±0.78kN; (b) The voltage of the cell drops by at least 100 mV; or (c) The cell is deformed by 50% or more of its original thickness. Once the maximum pressure has been obtained, the voltage drops by 100mV or more, or the cell is deformed by at least N/A 50% of its original thickness, the pressure shall be released. 直到发生下述三个条件中的任一条件: (a) 作用力达到 13kN±0.78kN; (b) 电芯电压下降至少 100mV; 或 (c) 电芯厚度和最初比较变形 50%以上。 一旦达到最大压力, 电压降超过 100 mV 或者电芯变形至少 50%,压力应该解除。 A prismatic or pouch cell shall be crushed by applying the force to the widest side. A button/coin cell shall be crushed by applying the force on its flat surface. For cylindrical cells, the crush force shall be applied perpendicular to longitudinal axis. N/A 棱形或袋装电芯应该在宽面施加挤压力,纽扣/硬币电芯应该在 平面施加挤压力。圆柱型电芯应该在长轴的垂直方向施加挤压 力。 Each test cell or component cell is to be subjected to one crushed only. The test sample shall be observed for a further 6h. The test shall be conducted using test cell or component N/A cells that have not previously been subjected to others tests. 每一个测试的电芯或元件电芯只进行一次挤压,测试后再观察 6h. 用于测试的电芯或元件电芯之前没有进行过其它的测试。

Result of Impact and Crush /重物冲击和挤压试验结果

TRF No.: UN38.3 Rev.6 amend1 00

38.3.4.6.4

P



Report No. / 报告编号: HLDY20200814U02 UN Manual of Tests and Criteria ST/SG/AC.10/11/Rev.6, amend1, section 38.3. 联合国《关于危险货物运输的建议书试验和标准手册》ST/SG/AC.10/11/Rev.6, amend1, section 38.3. Clause Requirement Result Verdict 条款 要求 结果 判断 Results: External temperature does not exceed 170°C and there is no disassembly and no fire during the test and within six See the TABLE: hours after this test. P 38.3.4.6 试验结果:外部温度不超过 170°C,试验期间和试验后 6 小时 内, 无解体或起火现象。 38.3.4.7 Overcharge/过充电 N/A Applicable to rechargeable lithium cell/battery with overcharge protection. 适用于具有过充电保护功能的可充电锂电芯/电池。 The charge current shall be twice the manufacturers' recommended maximum continuous charge current. N/A 充电电流应为制造商推荐的最大持续充电电流的两倍。 When the manufacturer's recommended charge voltage is not more than 18V, the minimum voltage of the test shall be the lesser of two times the maximum charge voltage of N/A the battery or 22V. 制造商建议的充电电压不大于 18 伏时,实验的最小电压应 是电池组最大充电电压的两倍或 22 伏两者中的较小者。 When the manufacturer's recommended charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times maximum charge voltage. N/A 制造商建议的充电电压大于 18 伏时,实验的最小电压应是 最大充电电压的 1.2 倍。 Tests are to be at ambient temperature. The duration of the test shall be 24 hours N/A 测试在室温下进行,测试时间为 24h. Results: there is no disassembly and no fire during the test and See the TABLE: within seven days after this test N/A 38.3.4.7 试验结果: 试验期间和试验后7天内, 无解体或起火现象。 38.3.4.8 Forced Discharge/强制放电 P Each cell shall be forced discharged at ambient temperature by connecting it in series with a 12V D.C, power supply at an initial current equal to the maximum discharge current specified by the manufacturer. P 在环境温度下,将单个电芯连接在 12V 的直流电源上进行强制 放电,此直流电源提供给每个电芯的初始电流为制造厂指定的最 大放电电流。 Results: there is no disassembly and no fire during the test and

TRF No.: UN38.3 Rev.6 amend1 00

within seven days after this test

试验结果: 试验期间和试验后7天, 无解体或起火现象。

P

See the TABLE:

38.3.4.8



ABLE: 38.3	3.4.1 Altitude	simulation 高	度模拟				Pass
	Before test		After test		Mass loss	Residual	
MODEL	Mass(g)	OCV(V)	Mass(g)	OCV(V)	(%)	OCV (%)	Results
		11	Fully charged	at first cycle			
C1#	36.111	4.18	36.108	4.18	0.008	100.00	Pass
C2#	36.235	4.17	36.232	4.17	0.008	100.00	Pass
C3#	36.275	4.17	36.273	4.16	0.006	99.76	Pass
C4#	36.449	4.18	36.446	4.17	0.008	99.76	Pass
C5#	36.183	4.17	36.180	4.17	0.008	100.00	Pass
			Fully charged	after 25 cycle	es		
C6#	36.564	4.18	36.561	4.18	0.008	100.00	Pass
C7#	36.620	4.18	36.618	4.17	0.005	99.76	Pass
C8#	36.273	4.17	36.270	4.17	0.008	100.00	Pass
C9#	36.347	4.18	36.344	4.18	0.008	100.00	Pass
C10#	36.228	4.17	36.226	4.17	0.006	100.00	Pass

Results: Pass = no leakage, no venting, no disassembly, no rupture, no fire, and the open circuit voltage drop not less than 90%

「ABLE: 38.3.4.2 Thermal test 温度试验						Pass	
MODEL	Befor	e test	After test		Mass loss	Residual	D
MODEL	Mass(g)	OCV(V)	Mass(g)	OCV(V)	(%)	OCV (%)	Results
			Fully charged	at first cycle			
C1#	36.108	4.18	36.092	4.10	0.044	98.09	Pass
C2#	36.232	4.17	36.216	4.10	0.044	98.32	Pass
C3#	36.273	4.16	36.256	4.09	0.047	98.32	Pass
C4#	36.446	4.17	36.431	4.10	0.041	98.32	Pass
C5#	36.180	4.17	36.164	4.11	0.044	98.56	Pass
			Fully charged	after 25 cycle	es		
C6#	36.561	4.18	36.544	4.10	0.044	98.09	Pass
C7#	36.618	4.17	36.603	4.11	0.044	98.56	Pass
C8#	36.270	4.17	36.255	4.10	0.047	98.32	Pass
C9#	36.344	4.18	36.328	4.11	0.041	98.33	Pass
C10#	36.226	4.17	36.211	4.10	0.044	98.32	Pass

Results: Pass = no leakage, no venting, no disassembly, no rupture, no fire, and the open circuit voltage drop not less than 90%



ABLE: 38.3.4.3 Vibration 振动						Pass	
MODEL	Befor	e test	After	test	Mass loss	Residual	
MODEL	Mass(g)	OCV(V)	Mass(g)	OCV(V)	(%)	OCV (%)	Results
			Fully charged	at first cycle			
C1#	36.092	4.10	36.090	4.09	0.006	99.76	Pass
C2#	36.216	4.10	36.214	4.10	0.006	100.00	Pass
C3#	36.256	4.09	36.254	4.09	0.006	100.00	Pass
C4#	36.431	4.10	36.428	4.10	0.008	100.00	Pass
C5#	36.164	4.11	36.162	4.10	0.006	99.76	Pass
			Fully charged	after 25 cycle	es		
C6#	36.544	4.10	36.543	4.10	0.003	100.00	Pass
C7#	36.603	4.11	36.601	4.10	0.005	99.76	Pass
C8#	36.255	4.10	36.254	4.10	0.003	100.00	Pass
C9#	36.328	4.11	36.326	4.10	0.006	99.76	Pass
C10#	36.211	4.10	36.208	4.09	0.008	99.76	Pass

Results: Pass = no leakage, no venting, no disassembly, no rupture, no fire, and the open circuit voltage drop not less than 90%

ABLE: 38.3	3.4.4 Shock 冲	击					Pass
	Befor	e test	After test		Mass loss	Residual	
MODEL	Mass(g)	OCV(V)	Mass(g)	OCV(V)	(%)	OCV (%)	Results
			Fully charged	at first cycle			
C1#	36.090	4.09	36.089	4.09	0.003	100.00	Pass
C2#	36.214	4.10	36.212	4.10	0.006	100.00	Pass
C3#	36.254	4.09	36.253	4.09	0.003	100.00	Pass
C4#	36.428	4.10	36.426	4.09	0.005	99.76	Pass
C5#	36.162	4.10	36.161	4.10	0.003	100.00	Pass
			Fully charged	after 25 cycle	es		
C6#	36.543	4.10	36.542	4.10	0.003	100.00	Pass
C7#	36.601	4.10	36.600	4.09	0.003	99.76	Pass
C8#	36.254	4.10	36.252	4.09	0.006	99.76	Pass
C9#	36.326	4.10	36.325	4.10	0.003	100.00	Pass
C10#	36.208	4.09	36.207	4.09	0.003	100.00	Pass

Results: Pass = no leakage, no venting, no disassembly, no rupture, no fire, and the open circuit voltage drop not less than 90%



ABLE: 38.3.4	.5 External Short-circu	it 外部短路		Pass
MODEL	Ambient(°C) (At 57± 4°C)	Testing resistance (mΩ)	Max. External Temperature(°C)	Results
		Fully charged at first cycle		
C1#	57.5	86.4	134.8	Pass
C2#	57.5	84.5	137.2	Pass
C3#	57.5	85.7	135.5	Pass
C4#	57.5	87.2	136.9	Pass
C5#	57.5	86.8	133.3	Pass
		Fully charged after 25 cycles		
C6#	57.2	85.2	135.4	Pass
C7#	57.2	86.1	132.7	Pass
C8#	57.2	84.9	132.4	Pass
C9#	57.2	83.9	134.5	Pass
C10#	57.2	85.8	134.8	Pass

TABLE: 38.3.4.6 Impact 重物冲击 TABLE: 38.3.4.6 Crush 挤压					Pass N/A
50% of the design rated capacity at first cycle		50% of the design rated capacity after		er 25 cycles	
C11#	138.3	Pass	C16#	142.2	Pass
C12#	141.2	Pass	C17#	138.9	Pass
C13#	142.5	Pass	C18#	143.3	Pass
C14#	139.6	Pass	C19#	141.0	Pass
C15#	140.1	Pass	C20#	139.3	Pass




Report No. / 报告编号: HLDY20200814U02

TABLE: 38.3.4.7 Overcharge 过度充电					N/A
The test current = / The test voltage = /					
Fully charged at first cycle Fully charged after 25 cyc				cles	
1	1	1	1	1	1
1	1	1	1	- 1	1
- 1	1	1	_ /	1	1
1	1	1	1	1	1

ABLE: 38.3.4.8 Forced discharge 强制放电					Pass
MODEL	OCV(V)	Results	MODEL	OCV(V)	Results
Fully	discharged at first	cycle	Fully	discharged after 25	cycles
C21#	3.131	Pass	C31#	3.196	Pass
C22#	3.224	Pass	C32#	3.214	Pass
C23#	3.222	Pass	C33#	3.210	Pass
C24#	3.188	Pass	C34#	3.199	Pass
C25#	3.217	Pass	C35#	3.187	Pass
C26#	3.215	Pass	C36#	3.198	Pass
C27#	3.203	Pass	C37#	3.202	Pass
C28#	3.202	Pass	C38#	3.215	Pass
C29#	3.198	Pass	C39#	3.218	Pass
C30#	3.211	Pass	C40#	3.221	Pass





-- End of Report --



Important Note

注意事项

 The test report is invalid without the special seal for testing and Paging seal of Guangzhou MCM Certification & Testing Co., Ltd.

本报告无检测单位检测专用章、骑缝章无效。

Nobody is allowed to photocopy or partly photocopy this test report without written permission of Guangzhou MCM Certification & Testing Co., Ltd.

未经本试验室书面同意,不得部分地复制本报告。

3. The test report is invalid without the signatures of Approver, Checker and Tester.

本报告无批准人、审核人及检测人签名无效。

4. The test report is invalid if altered.

本报告涂改无效。

Objections to the test report must be submitted to Guangzhou MCM Certification & Testing Co.,
 Ltd. within 15 days.

对检测报告若有异议,应于收到报告之日起十五天内向检测单位提出。

6. The test report is valid for the tested samples only.

本报告仅对来样负责。

7. The testing item of this report is not in the scope of CMA. Do not have the impartial function. 本报告检测项目不在 CMA 范围内,不具有公正性的作用。

8. As for the test result, "N/A" means "not applicable", "P" means "pass" and "F" means "fail".

本检测结果中"N/A"表示"不适用", "P"表示"通过", "F"表示"不通过"

Laboratory: Guangzhou MCM Certification & Testing Co., Ltd.

检测单位: 广州邦禾检测技术有限公司

Address: 1 F No.13, Zhong San Section, ShiGuang Road, Panyu District, Guangzhou

City, Guangdong Province, China.

地址: 中国广州市番禺区市广路钟三路段 13 号之一

Tel/电话: 0086-20-34777662

Email/电子邮箱: mark.miao@mcmtek.com

Web/公司网址: Http://www.mcmtek.com